



Advanced Ceramic Technologies

510 Ninth Avenue, Beaver Falls, PA 15010

Telephone: 724 843 8300

Fax: 724 843 5644

Email: sales@mcdanelceramics.com

Web: www.mcdanelceramics.com

99.8% ALUMINA

TYPE C799 TO IEC 60672

Composition

Alumina	Al ₂ O ₃	99.82%
Silica	SiO ₂	0.06%
Calcia	CaO	0.04%
Magnesia	MgO	0.035%
Iron Oxide	Fe ₂ O ₃	0.025%
Sodium Oxide	Na ₂ O	0.008%
Titania	TiO ₂	0.004%
Chromic Oxide	Cr ₂ O ₃	0.003%
Potassium Oxide	K ₂ O	0.001%
Boron Oxide	B ₂ O ₃	0.001%

Physical Properties

Bulk Density	Open Porosity	Flexural Strength		Compressive Strength
		20°C	1000°C	20°C
3.91 g/cm ³	0%	380 Mpa	165 Mpa	2650 Mpa
244 lbs/ft ³	0%	55 ksi	24 ksi	384 ksi

Thermal Properties

Conductivity		Expansion Coefficient	Max Use Temperature (no load)
20°C	800°C		
30 W/m ^{°K}	8.2 W/m ^{°K}	8.4 x 10 ⁻⁶ /C°	1750°C
208 BTU.in/ft ² .hr°F	57 BTU.in/ft ² .hr°F	4.7 x 10 ⁻⁶ /F°	3182°F

These values represent typical properties of standard materials.

Values should be used only for comparison and should not be used as a warranty.